

## Orco Flex Finish 40™

**Orco Flex Finish 40<sup>™</sup>** is a modified nonionic polyvinyl acetate emulsion for use in coating and finishing where a strong but flexible film is desired and is especially useful when high percentages of Poly Vinyl Acetate causes "cracking off."

## **Physical Properties**

Form	Pourable white fluid
Ionic charge	nonionic
Specific Gravity	1.06
Stability	stable in pH range of 3.5-9.0; Keep from freezing
рН	3.5 - 4.5

## Applications

Applicable to all fibers

## Procedures

For application where fullness of hand is desired without the usual harshness of conventional Poly Vinyl Acetates, 5 - 10% **Orco Flex Finish 40<sup>m</sup>** on weight of goods may be padded on material at room temperature with the usual drying temperature of 175°F - 250°F(79-120°C).

Rhode Island Division 65 Valley Street East Providence, RI 02914 Tel: 800-556-6784 Tel: 401-434-3300 Fax: 401-438-8136 North Carolina Division 1015 Concord Parkway North Concord, NC 28027 Tel: 800-783-6955 Tel: 704-786-1118 Fax: 704-786-2415 Shanghai Division Tel: 021-56630119 Fax: 021-56329220

www.organicdye.com