

ECCOBOND™ OLF

CLASSIFICATION: Low VOC, crosslinkable, waterborne aliphatic urethane polymer dispersion.

PROPERTIES:

| | |
|--------------|---|
| Appearance | - Low viscosity, water-white dispersion |
| % Solids | - 40% |
| lbs/gallon | - 8.9 |
| pH | - 8.0 ± 0.5 |
| VOC (lb/gal) | - 1.2 |

DRY FILM PROPERTIES:

| | |
|------------------|------------|
| Elongation | - 400% |
| Tensile Strength | - 5000 psi |
| Modulus @ 100% | - 700 psi |
| Modulus @ 500% | - 1700 psi |

GENERAL COMMENTS: ECCOBOND OLF is a uniquely compounded aliphatic urethane aqueous dispersion. This product produces excellent chemical and water resistance with excellent adhesion to PVC, vinyls, leathers, nylon and polyester fibers and films.

ECCOBOND OLF is excellent as a clear coat for leather, paper, plastics and synthetics where a tough, flexible coating is desired.

ECCOBOND OLF will cure at room temperature, but curing at 250-300°F will accelerate cured hardness.

Where additional film hardness or to reduce elongation and increase tensile strength, add 5-15% **ECC REZ U-7002** on the total weight of **ECCOBOND OLF**.

Information contained in this technical data sheet is up-to-date and correct to the best of Organic Dyes & Pigments' knowledge at the date of issue and are subject to change. As Organic Dyes & Pigments LLC cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. Organic Dyes & Pigments will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given. Released: 07/19 RY