

## Physical Properties & Resin Suitability for

### OrcoPlast™ Solvent Dyes

OrcoPlast™ solvent soluble dyes are applicable primarily to plastics. Other mediums dyeable by OrcoPlast™ dyes include aromatic hydrocarbons, oils, fats, waxes, and wood stains.

Page 1 of 2

Identification			Physical Properties				Resin Suitability							
OrcoPlast™	Shade	Color Index	Chemical Character	Specific Gravity (g/cm <sup>3</sup> )	Melting Point (°C)	Light fastness in Polystyrene	Poly styrene	Rigid PVC	PolyPropylene	PMMA	ABS SAN	Poly ester	Poly carbonate	Poly amide
Nigrosine SB		SBk 5		1.30										
Nigrosine NB Base		SBk 7	Azine	1.25	142	5-6	x	x		x	x			
Blue B 200%		SB 35	Anthraquinone	1.40	115	7	x	x		x		x		
Blue AP		SB 36	Anthraquinone	1.25	169-173	7				x				
Blue N		SB 59	Anthraquinone	1.72	208-216	7	x	x		x				
Blue ERO		SB 102	Anthraquinone	1.37	142	5-7	x	x		x	x	x		
Blue 2B		SB 104	Anthraquinone	1.30	240	7	x	x	x	x	x	x	x	x
Blue 2R		SB 128	Anthraquinone	1.51	266-270	7-8	x	x		x	x			
Green B		SG 3	Anthraquinone	1.35	213	6-7	x			x	x	x	x	x
Green 820		SG 28	Anthraquinone		200	6-7	x	x			x	x	x	
Orange PER		SO 60	Perinone	1.50	231-233	7-8	x	x		x	x	x	x	x
Orange Amber		SO 86	Anthraquinone	1.16	195-199	7	x			x				
Red SBRO		SR 23	Anthraquinone	1.20	198-202	5	x			x				
Red 4B		SR 24	Azo	1.18	80	7-8	x			x				
Oil Red GN		SR 26	Azo	1.50	220		x		x	x				
Red MX		SR 27	Azo	1.50	250	5-6	x		x	x				
Red 5		SR 52	Anthraquinone	1.37	280	5-7	x	x	x	x	x	x	x	x
Red SBA		SR 111	Anthraquinone	1.40	163-172	6-7	x	x		x	x	x	x	x
Red SBP		SR 135	Perinone	1.40	316-318	6-7	x			x	x	x	x	x

## Physical Properties & Resin Suitability for

### OrcoPlast™ Solvent Dyes

Page 2 of 2

<b>Red SBSE</b>		SR 168	Anthraquinone	1.40	176	7	x	x		x	x		x	x
<b>Red SBSN</b>		SR 169	Anthraquinone	1.80	164-170	6-7	x	x		x	x		x	x
<b>Red SBPN</b>		SR 179	Perinone	1.46	255	6	x			x	x	x	x	x
<b>Red SBTO</b>		SR 207	Anthraquinone	1.40	236-251	3-5	x	x		x	x	x	x	x
<b>Methyl Violet Base</b>		SV 8	Anthraquinone	1.35	180-183	6	x			x				x
<b>Violet IRS</b>		SV 13	Anthraquinone	1.35	180-184	6	x			x			x	
<b>Violet M</b>		SV 14	Anthraquinone	1.89	215	5-7	x			x	x	x		x
<b>Violet R</b>		SV 26	Anthraquinone	1.47	186	7	x	x	x	x	x	x	x	x
<b>Violet 3B</b>		SV 38	Anthraquinone	1.94	302	5-7	x	x		x		x		
<b>Yellow O</b>		SY 33	Quinoline	1.87	238-241	6	x	x		x	x	x	x	x
<b>Yellow EF</b>		SY 56	Azo	1.29	86		x			x				
<b>Yellow SBC</b>		SY 72	Azo	1.03	176	6	x		x	x				
<b>Yellow 4G</b>		SY 93	Monomethine	1.35	181	7	x	x		x	x		x	
<b>Yellow G</b>		SY 114	Naphthalamide	1.49	264	7	x	x		x	x	x	x	
<b>Yellow GS</b>		SY 163	Anthraquinone	1.30	182-186	6-7	x		x	x	x	x	x	x
<b>Yellow TG</b>		SY 167	Anthraquinone	1.95	188	6-7	x			x		x	x	x
<b>Fluorescent Green E</b>		SG 5	Anthraquinone	1.42	205	8	x			x			x	x
<b>Fluorescent Orange FC</b>		SO 63	Thioxanthrene	1.73	310	7	x	x	x	x	x	x	x	x
<b>Fluorescent Red G</b>		SR 277	Anthraquinone	1.70	144-146	5-7	x	x		x	x	x	x	x
<b>Fluorescent Red 5B</b>		VR 41	Anthraquinone	1.00	296	7	x			x	x		x	x
<b>Fluorescent Yellow 10GN</b>		DpY 82	Anthraquinone	1.50	236-238	5-7	x			x	x	x	x	x
<b>Fluorescent Yellow 3GF</b>		SY 98	Xanthene		220	7	x			x	x	x	x	x
<b>Fluorescent Yellow FG</b>		SY 43	Naphthalamide	1.30	124-128	1-3	x			x				
<b>Fluorescent Yellow 6G</b>		SY 44	Naphthalamide	1.86	230		x			x				

Information contained in this technical data sheet is up-to-date and correct to the best of Organic Dyes & Pigments' knowledge at the date of issue and are subject to change. As Organic Dyes & Pigments LLC cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. Organic Dyes & Pigments will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given.

Released: 07/19 RY