

Physical Properties & Resin Suitability for OrcoSolve™ Solvent Dyes

OrcoSolve™ solvent soluble dyes are applicable primarily to plastics. Other mediums dyeable by OrcoSolve™ dyes include aromatic hydrocarbons, oils, fats, waxes, and wood stains.

Page 1 of 2

Identification			Physical Properties				Resin Suitability							
OrcoSolve™	Shade	Color Index	Chemical Character	Specific Gravity (g/cm ³)	Melting Point (°C)	Light fastness in Polystyrene	Poly styrene	Rigid PVC	PolyPropylene	PMMA	ABS SAN	Poly ester	Poly carbonate	Poly amide
Nigrosine SB		SBk 5		1.30										
Nigrosine NB Base		SBk 7	Azine	1.25	142	5-6	x	x		x	x			
Blue B 200%		SB 35	Anthraquinone	1.40	115	7	x	x		x		x		
Blue AP		SB 36	Anthraquinone	1.25	169-173	7				x				
Blue N		SB 59	Anthraquinone	1.72	208-216	7	x	x		x				
Blue ERO		SB 102	Anthraquinone	1.37	142	5-7	x	x		x	x	x		
Blue 2B		SB 104	Anthraquinone	1.30	240	7	x	x	x	x	x	x	x	x
Blue 2R		SB 128	Anthraquinone	1.51	266-270	7-8	x	x		x	x			
Green B		SG 3	Anthraquinone	1.35	213	6-7	x			x	x	x	x	x
Green 820		SG 28	Anthraquinone		200	6-7	x	x			x	x	x	
Orange PER		SO 60	Perinone	1.50	231-233	7-8	x	x		x	x	x	x	x
Orange Amber		SO 86	Anthraquinone	1.16	195-199	7	x			x				
Red SBRO		SR 23	Anthraquinone	1.20	198-202	5	x			x				
Red 4B		SR 24	Azo	1.18	80	7-8	x			x				
Oil Red GN		SR 26	Azo	1.50	220		x		x	x				
Red MX		SR 27	Azo	1.50	250	5-6	x		x	x				
Red 5		SR 52	Anthraquinone	1.37	280	5-7	x	x	x	x	x	x	x	x
Red SBA		SR 111	Anthraquinone	1.40	163-172	6-7	x	x		x	x	x	x	x
Red SBP		SR 135	Perinone	1.40	316-318	6-7	x			x	x	x	x	x

Physical Properties & Resin Suitability for

OrcoSolve™ Solvent Dyes

Page 2 of 2

Red SBSE		SR 168	Anthraquinone	1.40	176	7	x	x		x	x		x	x
Red SBSN		SR 169	Anthraquinone	1.80	164-170	6-7	x	x		x	x		x	x
Red SBPN		SR 179	Perinone	1.46	255	6	x			x	x	x	x	x
Red SBTO		SR 207	Anthraquinone	1.40	236-251	3-5	x	x		x	x	x	x	x
Methyl Violet Base		SV 8	Anthraquinone	1.35	180-183	6	x			x				x
Violet IRS		SV 13	Anthraquinone	1.35	180-184	6	x			x			x	
Violet M		SV 14	Anthraquinone	1.89	215	5-7	x			x	x	x		x
Violet R		SV 26	Anthraquinone	1.47	186	7	x	x	x	x	x	x	x	x
Violet 3B		SV 38	Anthraquinone	1.94	302	5-7	x	x		x		x		
Yellow O		SY 33	Quinoline	1.87	238-241	6	x	x		x	x	x	x	x
Yellow EF		SY 56	Azo	1.29	86		x			x				
Yellow SBC		SY 72	Azo	1.03	176	6	x		x	x				
Yellow 4G		SY 93	Monomethine	1.35	181	7	x	x		x	x		x	
Yellow G		SY 114	Naphthalamide	1.49	264	7	x	x		x	x	x	x	
Yellow GS		SY 163	Anthraquinone	1.30	182-186	6-7	x		x	x	x	x	x	x
Yellow TG		SY 167	Anthraquinone	1.95	188	6-7	x			x		x	x	x
Fluorescent Green E		SG 5	Anthraquinone	1.42	205	8	x			x			x	x
Fluorescent Orange FC		SO 63	Thioxanthrene	1.73	310	7	x	x	x	x	x	x	x	x
Fluorescent Red G		SR 277	Anthraquinone	1.70	144-146	5-7	x	x		x	x	x	x	x
Fluorescent Red 5B		VR 41	Anthraquinone	1.00	296	7	x			x	x		x	x
Fluorescent Yellow 10GN		DpY 82	Anthraquinone	1.50	236-238	5-7	x			x	x	x	x	x
Fluorescent Yellow 3GF		SY 98	Xanthene		220	7	x			x	x	x	x	x
Fluorescent Yellow FG		SY 43	Naphthalamide	1.30	124-128	1-3	x			x				
Fluorescent Yellow 6G		SY 44	Naphthalamide	1.86	230		x			x				

Information contained in this technical data sheet is up-to-date and correct to the best of Organic Dyes & Pigments' knowledge at the date of issue and are subject to change. As Organic Dyes & Pigments LLC cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. Organic Dyes & Pigments will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given.

Released: 07/19 RY