

## OrcoSolve™ Solvent Dyes

### Physical Properties & Resin Suitability

OrcoSolve™ solvent soluble dyes are applicable primarily aromatic hydrocarbons, oils, fats, waxes, wood stains and plastics

Page 1 of 2

Identification			Physical Properties				Resin Suitability							
OrcoSolve™	Shade		Chemical Character	Specific Gravity (g/cm <sup>3</sup> )	Melting Point (°C)	Light fastness in Polystyrene	Poly styrene	Rigid PVC	PolyPropylene	PMMA	ABS SAN	Poly ester	Poly carbonate	Poly amide
Nigrosine SB				1.30										
Nigrosine NB Base			Azine	1.25	142	5-6	x	x		x	x			
Blue B 200%			Anthraquinone	1.40	115	7	x	x		x		x		
Blue AP			Anthraquinone	1.25	169-173	7				x				
Blue N			Anthraquinone	1.72	208-216	7	x	x		x				
Blue ERO			Anthraquinone	1.37	142	5-7	x	x		x	x	x		
Blue 2B			Anthraquinone	1.30	240	7	x	x	x	x	x	x	x	x
Blue 2R			Anthraquinone	1.51	266-270	7-8	x	x		x	x			
Green B			Anthraquinone	1.35	213	6-7	x			x	x	x	x	x
Green 820			Anthraquinone		200	6-7	x	x			x	x	x	
Orange PER			Perinone	1.50	231-233	7-8	x	x		x	x	x	x	x
Orange Amber			Anthraquinone	1.16	195-199	7	x			x				
Red SBRO			Anthraquinone	1.20	198-202	5	x			x				
Red 4B			Azo	1.18	80	7-8	x			x				
Red MX			Azo	1.50	250	5-6	x		x	x				
Red 5			Anthraquinone	1.37	280	5-7	x	x	x	x	x	x	x	x
Red SBA			Anthraquinone	1.40	163-172	6-7	x	x		x	x	x	x	x
Red SBP			Perinone	1.40	316-318	6-7	x			x	x	x	x	x



## Physical Properties & Resin Suitability for

### OrcoSolve™ Solvent Dyes

Page 2 of 2

<b>Red SBSE</b>		Anthraquinone	1.40	176	7	x	x		x	x		x	x
<b>Red SBSN</b>		Anthraquinone	1.80	164-170	6-7	x	x		x	x		x	x
<b>Red SBPN</b>		Perinone	1.46	255	6	x			x	x	x	x	x
<b>Red SBTO</b>		Anthraquinone	1.40	236-251	3-5	x	x		x	x	x	x	x
<b>Methyl Violet Base</b>		Anthraquinone	1.35	180-183	6	x			x				x
<b>Violet IRS</b>		Anthraquinone	1.35	180-184	6	x			x			x	
<b>Violet M</b>		Anthraquinone	1.89	215	5-7	x			x	x	x		x
<b>Violet R</b>		Anthraquinone	1.47	186	7	x	x	x	x	x	x	x	x
<b>Violet 3B</b>		Anthraquinone	1.94	302	5-7	x	x		x		x		
<b>Yellow EF</b>		Azo	1.29	86		x			x				
<b>Yellow SBC</b>		Azo	1.03	176	6	x		x	x				
<b>Yellow 4G</b>		Monomethine	1.35	181	7	x	x		x	x		x	
<b>Yellow G</b>		Naphthalamide	1.49	264	7	x	x		x	x	x	x	
<b>Yellow GS</b>		Anthraquinone	1.30	182-186	6-7	x		x	x	x	x	x	x
<b>Yellow TG</b>		Anthraquinone	1.95	188	6-7	x			x		x	x	x
<b>Fluorescent Green E</b>		Anthraquinone	1.42	205	8	x			x			x	x
<b>Fluorescent Orange FC</b>		Thioxanthrene	1.73	310	7	x	x	x	x	x	x	x	x
<b>Fluorescent Red G</b>		Anthraquinone	1.70	144-146	5-7	x	x		x	x	x	x	x
<b>Fluorescent Red 5B</b>		Anthraquinone	1.00	296	7	x			x	x		x	x
<b>Fluorescent Yellow 10GN</b>		Anthraquinone	1.50	236-238	5-7	x			x	x	x	x	x
<b>Fluorescent Yellow 3GF</b>		Xanthene		220	7	x			x	x	x	x	x
<b>Fluorescent Yellow FG</b>		Naphthalamide	1.30	124-128	1-3	x			x				
<b>Fluorescent Yellow 6G</b>		Naphthalamide	1.86	230		x			x				

Information contained in this technical data sheet is up-to-date and correct to the best of Organic Dyes & Pigments' knowledge at the date of issue and are subject to change. As Organic Dyes & Pigments LLC cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. Organic Dyes & Pigments will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given.

Released: 09/23 RY

