



## ORCOBRITE™ & ORCOSPERSE™ Organic Aqueous Pigment Dispersions

| Shade   |        | Product Name <sup>M</sup>            | Light Fastness (Rating)<br>Blue Wool Method ISO105-B02 (1-8) |        | Hi-Temperature Stable<br>(60-90 sec) |
|---------|--------|--------------------------------------|--|--------|--------------------------------------|
| 100 g/l | 10 g/l |                                      | 100 g/l  | 10 g/l |                                      |
|         |        | OrcoBrite Fluorescent Blue G 2065    | 3-5  |        | Heat Sensitive                       |
|         |        | OrcoBrite Fluorescent Green B 4010   | 3-5  |        | Heat Sensitive                       |
|         |        | OrcoBrite Fluorescent Orange RN 9018 | 3-5  |        | Heat Sensitive                       |
|         |        | OrcoBrite Fluorescent Magenta D55    | 3-5  |        | Heat Sensitive                       |
|         |        | OrcoBrite Fluorescent Pink BN 6027   | 3-5  |        | Heat Sensitive                       |
|         |        | OrcoBrite Fluorescent Red FP 6003    | 3-5  |        | Heat Sensitive                       |
|         |        | OrcoBrite Fluorescent Yellow GN 9026 | 3-5  |        | Heat Sensitive                       |
|         |        | Orcosperse Black 2835                | 8  | 8      | Stable to 375° F                     |
|         |        | Orcosperse Blue 2GN 2025             | 8  | 8      | Stable to 375° F                     |
|         |        | Orcosperse Blue 3GN 2010*            | 8  | 8      | Stable to 375° F                     |
|         |        | Orcosperse Royal Blue RN 2008        | 8  | 8      | Stable to 375° F                     |
|         |        | Orcosperse Green BN 4009             | 8  | 8      | Stable to 375° F                     |
|         |        | Orcosperse Magenta LDN 6141          | 8  | 7-8    | Stable to 375° F                     |
|         |        | Orcosperse Scarlet LDN 2949          | 8  | 7      | Stable to 375° F                     |
|         |        | Orcosperse Scarlet 6019              | 6-7  | 5-6    | Stable to 375° F                     |
|         |        | Orcosperse Red OC-2                  | 7  | 5-6    | Stable to 375° F                     |
|         |        | Orcosperse Pink LBN 6032             | 8  | 7-8    | Stable to 375° F                     |
|         |        | Orcosperse Violet 4BN 3030           | 8  | 8      | Stable to 375° F                     |
|         |        | Orcosperse Orange 1697               | 3-4  | 2-3    | Stable to 375° F                     |
|         |        | Orcosperse Brown 8400                | 7  | 6      | Stable to 375° F                     |
|         |        | Orcosperse Yellow HR Conc6           | 7  | 6      | Stable to 375° F                     |
|         |        | Orcosperse Yellow 9014               | 5  | 3-4    | Stable to 375° F                     |
|         |        | Orcosperse Yellow 5G Conc            | 7  | 6      | Stable to 375° F                     |
|         |        | Orcosperse White SGL 8002            | 8  | 8      | Stable to 375° F                     |

Actual dye samples should be evaluated in the chemical system or medium in which they are to be used for accurate shade and physical property results. Shades shown on print material and computer monitors are for general reference only as they are inherently inaccurate due to calibration variations and technical limitations of monitors and printers. Date: 03/24 RY

